

Data Sheet

Type Number:	55750	
Sytem:	Nickel Metal Hydride / KOH Electrolyte	
Nominal Voltage [V]:	1.2	
Nominal Capacity C [mAh]:	500	
Typical Capacity C [mAh]:	510	
	at 100 mA / 1.00 V	
Weight, approx. [g]	14.0	
Dimensions [mm]:	min.	max.
Length [l]:	24.0	24.2
Width Facing [w]:	33.9	34.1
Height [h]:	6.3	6.5

UL Recognition:	MH13654	
Coding:	Manufacturing 5 digit code (123 = day / 4 = year / 5 = version)	

Temperature Ranges [°C]	min.	max.
Storage: less than 30 days	-40	85
Discharge:	-20	85
Charge:	0	85

Charging Method:	
Normal Charging:	50 mA for 14 - 16 h
Accelerated Charging (20°C):	150 mA for 4 h
Time controlled, voltage control recommended	
Fast Charging (0 - 55°C):	500 mA for h *
Trickle Charging:	5 - 15 mA

Overcharge (20°C):	15 mA continuous 50 mA up to 1 year
---------------------------	--

Charge Retention [%] at 20°C:	80
Capacity available after 1 month Storage at 20°C	

Internal Resistance [Ohm]:	0.1
at charged cells, 20°C, DC: 0.2 CA / 2 CA, (IEC 61951-2)	

Impedance [Ohm]:	0.020
Typical value at charged cells, 20°C, AC: 1 kHz, (IEC 61951-2)	

Typical Capacities [mAh]:	
at 500 mA / 0.9 V	400
at 1500 mA / 0.9 V	200

Max. Discharge Current (cont.) [mA]:	1500
Life Expectancy (typical):	
IEC Cycle:	1000 Cycles (IEC 61951-2)
Trickle Charge:	up to 5 years (20°C)
Trickle Charge:	up to 3 years (45°C)

* (-dv = 5-10 mv / cell; dT / dt = 0.7°C / min)

Capacities based on normal charging

The Netherlands



Elektrostraat 17
NL-7483 PG Haaksbergen

T: +31 (0)53 573 33 33
F: +31 (0)53 573 33 30
E: nl@texim-europe.com

Belgium



Zuiderlaan 14 bus 10
B-1731 Zellik

T: +32 (0)2 462 01 00
F: +32 (0)2 462 01 25
E: belgium@texim-europe.com

UK & Ireland



St. Mary's House, Church Lane
Carlton Le Moorland
Lincoln LN5 9HS

T: +44 (0)1522 789 555
F: +44 (0)845 299 22 26
E: uk@texim-europe.com

Germany North



Bahnhofstrasse 92
D-25451 Quickborn

T: +49 (0)4106 627 07-0
F: +49 (0)4106 627 07-20
E: germany@texim-europe.com

Germany South



Martin-Kollar-Strasse 9
D-81829 München

T: +49 (0)89 436 086-0
F: +49 (0)89 436 086-19
E: germany@texim-europe.com

Austria



Warwitzstrasse 9
A-5020 Salzburg

T: +43 (0)662 216 026
F: +43 (0)662 216 026-66
E: austria@texim-europe.com

Nordic region



Sdr. Jagtvej 12
DK-2970 Hørsholm

T: +45 88 20 26 30
F: +45 88 20 26 39
E: nordic@texim-europe.com

General information



info@texim-europe.com
www.texim-europe.com